

DEACON

T E C H S H E E T

Page 1 of 1

6329

Descriptions:	Two Part Rubber Sealant Compound
Temperature Range:	-60°F. to 500°F.
Applications:	Gasket coating, threads, or void fill. Mild steam, water applications, Acetic Acid, Mineral Oil, Natural Gas, Propane, various chemicals.
Characteristics:	Cures to a solid with good adhesion. Remains flexible from -60 degrees F. to 500 degrees F. with intermittent exposure to 600 degrees F.
Cure Time:	6.5 hours.
Base / Catalyst Ratio:	10 :1
Working Time:	45 minutes
Note:	For additional bridging can be mixed with Deacon Dry-Pak mixtures
Shelf Life:	Two years in closed containers. Store below 90°F.
Packaged:	One Pint Kits, One Quart Kits, and One Gallon Kits.

FOR INDUSTRIAL USE BY PROFESSIONALLY TRAINED PERSONNEL ONLY. CONSULT MSDS & TECH SHEET FOR ALL SAFETY, TECHNICAL, & WARRANTY INFORMATION BEFORE USE. **NOT RECOMMENDED FOR USE ON NUCLEAR APPLICATIONS**

Disclaimer: The information & recommendations of Deacon concerning these products is based upon laboratory tests, customer feedback, and experience and to the best of our knowledge and belief are true and accurate. As the conditions of use are beyond the control of Deacon Industries, Inc. the company assumes no liability for damage caused by this product other than the replacement of the product or refund of the purchase price. The responsibility for determining whether or not the product is suitable for use rest solely with the purchaser. Deacon Industries, Inc., recommends that the product be tested prior to use. This product is intended for a temporary repair and no agent, representative or employee of the company is authorized to alter this provision which relates to goods delivered, whether sold, delivered as samples or otherwise.

info@deacon-intlsales.com (800) 552-2896 or (724) 225-8008